

GARBA 178MO

1/4

Stainless spring wire. Similar to EN 1.4310 with increased tensile strength

GARBA 178Mo is a general-purpose austenitic stainless steel that is used for springs and other components requiring good fatigue resistance and good resistance against atmospheric corrosion. Addition of molybdenum increases the tensile strength as compared to GARBA 188 and also increases the resistance against localised and general corrosion.

CHEMISCHE ZUSAMMENSETZUNG

C (%)	Si (%)	Mn (%)	P max. (%)	S max. (%)	Cr (%)	Ni (%)	Mo (%)
0,05 - 0,15	2,00	2,00	0,045	0,015	16,00 - 19,00	6,00 - 9,50	0,80

MECHANISCHE EIGENSCHAFTEN

FÜR RUNDRAHT

GARBA 178M0

2/4

Durchmesser (mm)	Toleranz (mm)	Zugfestigkeit (N/mm ²)
0,30 - 0,65	±0,008	-
0,66 - 1,01	±0,010	-
1,02 - 2,26	±0,015	-
2,27 - 4,01	±0,020	-
4,02 - 6,26	±0,025	-
6,27 - 8,00	±0,030	-
0,30 - 0,40		2250 - 2590
0,41 - 0,50		2200 - 2530
0,51 - 0,65		2150 - 2470
0,66 - 0,80		2100 - 2420
0,81 - 1,00		2050 - 2360
1,01 - 1,25		2000 - 2300
1,26 - 1,50		1950 - 2240
1,51 - 1,75		1900 - 2190
1,76 - 2,00		1850 - 2130
2,01 - 2,50		1750 - 2010
2,51 - 3,00		1700 - 1960
3,01 - 3,50		1650 - 1900
3,51 - 4,25		1600 - 1840
4,26 - 5,00		1550 - 1780
5,01 - 6,00		1500 - 1730
6,01 - 7,00		1450 - 1670
7,01 - 8,00		1400 - 1610

GARBA 178M0

3/4

OBERFLÄCHENBESCHAFFENHEITEN

Surface performance

AC-surface 0.30–8.00 mm Ø. The AC-coating can be removed before heat treatment by using a 10-20% nitric acid pickle at room temperature.

PHYSIKALISCHE EIGENSCHAFTEN

E UND G ELASTIZITÄTSMODUL

Abt. 180 kN/mm² in drawn condition.
Abt. 185 kN/mm² after heat treatment.

E UND G SCHUBMODUL

Abt. 70 kN/mm² in drawn condition.
Abt. 73 kN/mm² after heat treatment.

WÄRMELEITFÄHIGKEIT

Temperature °C	20	100	200	400
W/(m*°C)	15.0	16.0	18.0	20.0

WIDERSTANDSFÄHIGKEIT

Temperature °C	20	100	200	300
nΩm	700	750	800	950

LÄNGENAUSDEHNUNG

Pro °C	30–100	30–200	30–400
x10 ⁻⁶	17.0	17.5	18.5

SPEZIFISCHE WÄRMEKAPAZITÄT

Temperature °C	20	100	200	400
J/(kg*°C)	440	480	520	560

GARBA 178M0

4/4

STANDARDS

NÄCHSTÄHNLICHE VERGLEICHBARE STAHLGÜTEN

EN/DIN 1.4310, AISI/SAE 302

NÄCHSTÄHNLICHE VERGLEICHBARE NORMEN

EN 10270-3, ASTM A313, BS 2056 302 S26

EMPFEHLUNGEN

WÄRMEBEHANDLUNG

As soon as possible after coiling, the springs should be stress relieved.
Recommended temperature for compression springs or tension springs without initial tension is approx. 420 °C for 0.5 - 4 hours.