

70 KD

1/3

Oil tempered SiCr-alloyed clutch and transmission spring wire

70 KD is especially intended for the manufacture of clutch and transmission springs and similar moderately high fatigue stressed springs. 70 KD S is a shaved version of 70 KD intended for applications with higher surface requirements. The material has good relaxation properties. The wire is manufactured in sizes from Ø 0.50 to 7.00 mm. Other wire sizes and shapes on request.

CHEMISCHE ZUSAMMENSETZUNG

C (%)	Si (%)	Mn (%)	P max. (%)	S max. (%)	Cr (%)
0,50 - 0,60	1,20 - 1,60	0,50 - 0,80	0,025	0,020	0,50 - 0,80

REINHEITSGRAD IM STAHL

Non-metallic inclusions:

Max. level 2 according to DIN 50602-M.

Corresponding standard: ASTM E-45-A.

70 KD

2/3

MECHANISCHE EIGENSCHAFTEN

1) Other wire sizes on request.

2) Ovality, i. e. the difference between the largest and smallest dimension of a cross section, is maximum half the tolerance range.

3) Conversion from tensile strength to hardness values can be calculated in standard ISO EN 18265. The tensile strength R_m within one coil does not vary more than 60 N/mm^2 .

4) Torsion test is carried out for assessing deformability. The fracture of the torsion test piece shall be smooth and perpendicular to the wire axis. The rupture shall show no longitudinal cracks.

FÜR RUNDdraHT

Durchmesser (mm)	Toleranz (mm)	Zugfestigkeit (N/mm ²)	Torsionen (l=300 mm, min. revs)	Brucheinschnürung (min. %)
0,50 - 0,80	±0,010	2080 - 2210	6	
0,81 - 1,30	±0,015	2080 - 2210	5	50
1,31 - 1,40	±0,015	2080 - 2210	5	50
1,41 - 1,60	±0,020	2080 - 2210	5	50
1,61 - 2,00	±0,020	2010 - 2160	5	50
2,01 - 2,50	±0,020	1960 - 2060	5	50
2,51 - 3,00	±0,020	1910 - 2010	4	50
3,01 - 3,20	±0,020	1910 - 2010	4	45
3,21 - 3,50	±0,025	1910 - 2010	4	45
3,51 - 4,50	±0,025	1860 - 1960	4	45
4,51 - 5,00	±0,025	1810 - 1910	3	45
5,01 - 5,60	±0,030	1810 - 1910	3	40
5,61 - 6,00	±0,035	1760 - 1860	3	40
6,01 - 7,00	±0,035	1760 - 1860		40

STRECKGRENZE

The proof stress $R_{p0.2}$ is min. $0.9 \times$ tensile strength of the wire.

70 KD

3/3

OBERFLÄCHENBESCHAFFENHEITEN

OBERFLÄCHENBESCHAFFENHEIT

Surface condition – non-destructive testing

In the standard size range 2.00 - 6.00 mm the wire is tested continuously in Eddy Current equipment ; for 70 KD a level of 60 microns and for 70 KD S of 40 microns.

Surface condition – end sample test

The wire is end sample tested by means of etch testing and binocular inspection as well as microscopical inspection of the material structure. Max. permissible depth of partial surface decarburization and surface defects, 1.3% x wire diameter. No complete decarburization allowed.

PHYSIKALISCHE EIGENSCHAFTEN

E UND G ELASTIZITÄTSMODUL

206 kN/mm²

E UND G SCHUBMODUL

79.5 kN/mm²

STANDARDS

NÄCHSTÄHNLICHE VERGLEICHBARE STAHLGÜTEN

EN TDSiCr, SIS 142090-05

NÄCHSTÄHNLICHE VERGLEICHBARE NORMEN

ASTM A1000 A, BS 2803 685A55ND

EMPFEHLUNGEN

WÄRMEBEHANDLUNG

As soon as possible after coiling, the springs should be stress relieved.

WARMVORSETZEN

After shot peening, the springs should be hot preset or stress relieved. In order to reach optimum fatigue and relaxation properties, the springs must be preset at an appropriate stress.

KUGELSTRAHLEN

In order to obtain optimum fatigue properties, the process time should be adjusted to get a complete treatment. Size of shots should be adapted to wire dimension, pitch and shot peening equipment. Shot peening of the inside of the spring coils is particularly critical.