

GARBAFLEX 174MN

Flat and shaped wire

GARBAFLEX 174Mn is an austenitic stainless wire, supplied in the cold rolled or annealed condition.

CHEMICAL COMPOSITION

C (%)	Si (%)	Mn (%)	P max. (%)	S max. (%)	Cr (%)	Ni (%)
0.15	1.00	5.50 - 7.50	0.045	0.030	16.00 - 18.00	3.50 - 5.50

MECHANICAL PROPERTIES

Tensile strength

As cold rolled max. 1900 N/mm².

As annealed max. 950 N/mm².

Yield strength

As annealed 300-450 N/mm².

FOR FLAT ROLLED WIRE

Width (mm)	Tolerance (mm)
2.00 - 5.00	±0.050
5.01 - 8.00	±0.070
8.01 - 10.00	±0.100

Thickness (mm)	Tolerance (mm)
0.30 - 0.80	±0.015
0.81 - 1.00	±0.019
1.01 - 1.60	±0.025

FOR SHAPED WIRE

GARBAFLEX 174MN

2/3

Width (mm)	Tolerance (mm)
-1.50	±0.020
1.51 - 3.00	±0.030
3.01 - 5.00	±0.040
5.01 - 7.00	±0.050
7.00 -	±0.060

ELONGATION

As annealed min. 40%.

MICROSTRUCTURE

Austenite.

CAMBER

Max. 5 mm measured on 1 m length.

SURFACE CONDITIONS

SURFACE

Bright. Surface defects max. 1% of thickness.

PHYSICAL PROPERTIES

E AND G MODULUS OF ELASTICITY

Abt. 180 kN/mm² in drawn condition.
Abt. 185 kN/mm² after heat treatment.

E AND G MODULUS OF SHEAR

Abt. 70 kN/mm² in drawn condition.
Abt. 73 kN/mm² after heat treatment.
Density: 7.90 kg/dm³.

GARBAFLEX 174MN

3/3

STANDARDS

NEAREST EQUIVALENT STEEL GRADES

EN/DIN 1.4371, AISI/SAE 201, JIS SUS 201

NEAREST EQUIVALENT STANDARDS

JIS G4309

ADDITIONAL

ADDITIONAL INFORMATION

Delivery form

On wooden spools. Max. 250 kg.