

STATO 70

1/3

Oil tempered SiCr-alloyed spring wire

STATO 70 is especially intended for the manufacture of springs exposed to static or moderately high fatigue stresses. The material has good relaxation properties.

The wire is manufactured in sizes from \emptyset 0.50 mm to 7.00 mm. Other wire sizes on request.

CHEMICAL COMPOSITION

C (%)	Si (%)	Mn (%)	P max. (%)	S max. (%)	Cr (%)
0.50 - 0.60	1.20 - 1.60	0.50 - 0.80	0.025	0.025	0.50 - 0.80

STATO 70

2/3

MECHANICAL PROPERTIES

1) Other wire sizes on request.

2) Ovality, i. e. the difference between the largest and smallest dimension of a cross section, is maximum half the tolerance range.

3) Conversion from tensile strength to hardness values can be calculated in standard ISO EN 18265. The tensile strength R_m within one coil does not vary more than 70 N/mm^2 .

FOR ROUND WIRE

Diameter (mm)	Tolerance (\pm mm)	Tensile Strength (N/mm^2)	Reduct. of area (min. %)
0.50 - 0.80	0.010	2100 - 2300	
0.81 - 1.00	0.015	2100 - 2300	50
1.01 - 1.40	0.020	2060 - 2260	50
1.41 - 1.60	0.020	2040 - 2220	50
1.61 - 2.00	0.025	2000 - 2180	40
2.01 - 2.50	0.025	1970 - 2140	50
2.51 - 2.70	0.025	1950 - 2100	50
2.71 - 3.00	0.030	1910 - 2100	50
3.01 - 3.50	0.030	1900 - 2060	45
3.51 - 4.00	0.030	1870 - 2030	45
4.01 - 4.50	0.035	1860 - 2020	45
4.51 - 5.00	0.035	1830 - 1980	45
5.01 - 5.60	0.035	1800 - 1950	40
5.61 - 6.50	0.040	1780 - 1930	40
6.51 - 7.00	0.040	1740 - 1890	35

YIELD POINT

The proof stress $R_{p0.2}$ is min. $0.9 \times$ tensile strength of the wire.

STATO 70

3/3

SURFACE CONDITIONS

SURFACE CONDITION

Surface condition – end sample test

The wire is end sample tested by means of etch testing and binocular inspection as well as microscopical inspection of the material structure.

Max. permissible depth of partial surface decarburization and surface defects, 1.5% x wire diameter. No complete decarburization allowed.

PHYSICAL PROPERTIES

E AND G MODULUS OF ELASTICITY

206 kN/mm²

E AND G MODULUS OF SHEAR

79.5 kN/mm²

STANDARDS

NEAREST EQUIVALENT STEEL GRADES

EN FDSiCrV, SIS 142090-05

NEAREST EQUIVALENT STANDARDS

ASTM A401, BS 2803 685A55HS, JIS G3561 SWOSC-V

RECOMMENDATIONS

HEAT TREATMENT

As soon as possible after coiling, the springs should be stress relieved.

HOT PRESETTING

After shot peening, the springs should be hot preset or stress relieved. In order to reach optimum fatigue and relaxation properties, the springs must be preset at an appropriate stress.

SHOT PEENING

In order to obtain optimum fatigue properties, the process time should be adjusted to get a complete treatment. Size of shots should be adapted to wire dimension, pitch and shot peening equipment. Shot peening of the inside of the spring coils is particularly critical.